

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009

Revised: [April 27, 2017](#)

Density tests using cores shall be obtained at the frequency specified in the Hot Mix Asphalt Quality Control for Performance (QCP) and Pay for Performance (PFP) Using Percent within Limits special provisions. The random test locations shall be determined as follows:

- A) The random core locations shall be taken at the randomly selected test location within each density testing interval. The random test location will be determined by the Engineer using the “Random Numbers” table as specified herein or an approved software program. This may be performed each day or predetermined for the project. Regardless of when the values are determined, the values are to be considered confidential and are not to be disclosed to anyone outside of the Department. Disclosing the information prior to finish rolling would be in direct violation of federal regulations.

Each core location shall be randomly located both longitudinally and transversely within each density testing interval. Each core location within the density testing interval shall be determined with two random numbers. The first random number is used to determine the longitudinal distance to the nearest 1 ft into the density testing interval. The second random number is used to determine the transverse offset to the nearest 0.1 ft from the left edge of the **paving lane**. [In cases where paving is completed over multiple lanes in a single pass of one or more pavers to eliminate unconfined edges between lanes, the paving lane is defined as the total combined width of the lanes paved in that single pass.](#) The density intervals shall be every 0.1 mi. (160 m) for lift thicknesses of 3 in. (75 mm) or less and 0.05 mi. (80 m) for lift thicknesses greater than 3 in (75 mm) if the **paving lane** width is greater than 20 ft.

To determine the longitudinal location of a core, multiply the length of the prescribed density interval by the random number selected from the Random Number table. Determine the random transverse offset as follows:

1. PFP. The effective lane width of the pavement shall be used in calculating the transverse offset. The effective lane width is determined by subtracting 1.0 ft for each unconfined edge from the entire paved lane width (i.e. If a 12.0 ft wide paved lane has two unconfined edges, the effective lane width would be 10.0 ft.) Determine the transverse offset by multiplying the effective width by the random number selected from the Random Number table.

The transverse offset is measured from the left physical edge of the paved lane to locate the core on the pavement. If the left edge was unconfined, it will be omitted by adding 1.0 ft to the calculated transverse offset measurement.

Random locations that fall within 4.0 inches of a confined edge shall be moved to 4.0 inches off the edge. Areas outside the mainline pavement that are paved concurrently with the mainline pavement (i.e. three-ft wide left shoulders, driveways, etc.) are not considered part of the paved mainline mat. See PFP example calculation herein.

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009
Revised: [April 27, 2017](#)

The core density location for the outer 1.0 ft of an unconfined edge will be randomly selected within each 0.5 mile section for each unconfined edge. Longitudinal joint testing shall be located at a distance equal to the lift thickness or a minimum of 4.0 in. (100 mm), from each pavement edge. (i.e. for a 5 in. (125 mm) lift the near edge of the core barrel shall be within 5.0 in. (125 mm) from the edge of pavement.)

2. QCP. The entire width of the pavement shall be used in calculating the transverse offset. No offset movement is to be used for random locations that lie within 1.0 ft from an unconfined edge. Cores taken within 1.0 ft from an unconfined edge will have 2.0% density added for pay adjustment calculation purposes. Random locations that fall within 4.0 in. of an edge shall be moved to 4.0 in. off the edge. See QCP example calculation herein.

B) This process shall be repeated for all density intervals on a given project.

C) Moving Core Locations.

There are two scenarios in which random core locations may be moved longitudinally using the same random transverse offset. The first scenario is to avoid only the obstacles listed under Case 1 below. The second scenario is to avoid pavement defects in the surface being overlaid as described in Case 2 below.

- 1) Case 1. In the event the random core location will not allow the necessary compactive effort to be applied, the Engineer will adjust the longitudinal location of the core in order to avoid the obstacle. Using the same random transverse offset, the core location will be moved longitudinally, ± 15 feet to avoid the following obstacles only:
 - a) Structures or Bridge Decks
 - b) Detection loop or other pavement sensors
 - c) Manholes or other utility appurtenances
- 2) Case 2. In the event there are pavement defects in the surface being overlaid, the Contractor may place temporary markings on the shoulder to represent longitudinal locations where a defect is present. These pavement defect locations will be approved by the Engineer. If a random core location lands at the same longitudinal location as the temporary mark, the core will be moved 5 feet in the direction toward the paver at the same transverse offset. In the case of an asphalt scab (i.e. thin layer of less than 0.5 inches of asphalt pavement remaining after milling) the temporary markings shall show the extent or length of the defect. The core location will then be moved to a longitudinal distance 5 feet past the end of the defect toward the paver.

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009
Revised: [April 27, 2017](#)

D) Example Calculations.

PFP Example.

This **PFP** example illustrates the determination of the core locations within the first mile of a lot.

Given 1.5 in. thickness would require a density testing interval of 0.2 miles. The pavement consists of a 13.0 ft-wide mat with the left edge confined and the right edge unconfined. The random numbers for the longitudinal direction are 0.917, 0.289, 0.654, 0.347, and 0.777. The random numbers for the transverse direction are 0.890, 0.317, 0.428, 0.998, and 0.003.

The individual density test interval distances can be converted to the cumulative random distance using the following equation:

$$CD_n = [D \times (n - 1)] + R_n$$

Where:

n = the density interval number

CD = cumulative distance

D = density testing interval length (typically 1056 ft (0.2 mile))

R = Random distance within the given density testing interval

The longitudinal core locations are determined by multiplying the longitudinal random numbers by 1056 ft (0.2 mile). The transverse core locations are determined by multiplying the transverse random number by the effective width of the paved mat.

Determine the effective lane width by subtracting 1.0 ft, for each unconfined edge, from the entire paved lane width. In this case only the right edge is unconfined, so subtract 1.0 ft from the entire paved lane width of 13.0 ft.

$$\text{Effective Width} = 13.0 \text{ ft} \text{ minus } 1.0 \text{ ft} = 12.0 \text{ ft}$$

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009
Revised: [April 27, 2017](#)

The random location for the first mile measured from the beginning of the lot and the left (confined) edge of the paved mat are as follows:

Core #	Longitudinal Location	Cumulative Distance	Transverse Location
1	1056 x 0.917 = 968 ft	1056 x (1-1) + 968 = 968 ft	12.0 x 0.890 = 10.7 ft
2	1056 x 0.289 = 305 ft	1056 x (2-1) + 305 = 1361 ft	12.0 x 0.317 = 3.8 ft
3	1056 x 0.654 = 691 ft	1056 x (3-1) + 691 = 2803 ft	12.0 x 0.428 = 5.1 ft
4	1056 x 0.347 = 366 ft	1056 x (4-1) + 366 = 3534 ft	12.0 x 0.998 = 11.7 ft
5	1056 x 0.777 = 821 ft	1056 x (5-1) + 821 = 5045 ft	12.0 x 0.003 = 0.0 ft = 0.3 ft ^{1/}

1/ The 0.0 ft for Core #5 was moved in to 0.3 ft due to the 4 in. minimum from the edge requirement.

QCP Example.

This **QCP** example illustrates the determination of the core locations within the first mile of a project.

Given 1.5" thickness would require a density testing interval of 0.2 miles. The pavement consists of a 13.0 ft-wide mat with the left edge confined and the right edge unconfined. The random numbers for the longitudinal direction are 0.904, 0.231, 0.517, 0.253, and 0.040. The random numbers for the transverse direction are 0.007, 0.059, 0.996, 0.515, and 0.101.

The individual density test interval distances can be converted to the cumulative random distance using the following equation:

$$CD_n = [D \times (n - 1)] + R_n$$

Where:

- n = the density interval number
- CD = cumulative distance
- D = density testing interval length (typically 1056 ft (0.2 mile))
- R = Random distance within the given density testing interval

The longitudinal core locations are determined by multiplying the longitudinal random numbers by 1056 ft (0.2 mile). The transverse core locations are determined by multiplying the transverse random number by the width of the paved lane (13.0 ft).

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009
Revised: [April 27, 2017](#)

The random location for the first mile measured from the beginning of the lot and the left (confined) edge of the paved mat are as follows:

Core #	Longitudinal Location	Cumulative Distance	Transverse Location
1	$1056 \times 0.904 = 955 \text{ ft}$	$1056 \times (1-1) + 955 = 955 \text{ ft}$	$13.0 \times 0.007 = 0.1 \text{ ft} = \mathbf{0.3 \text{ ft}^{1/}}$
2	$1056 \times 0.231 = 244 \text{ ft}$	$1056 \times (2-1) + 244 = 1300 \text{ ft}$	$13.0 \times 0.059 = 0.8 \text{ ft}$
3	$1056 \times 0.517 = 546 \text{ ft}$	$1056 \times (3-1) + 546 = 2658 \text{ ft}$	$13.0 \times 0.996 = 13.0 \text{ ft} = \mathbf{12.7 \text{ ft}^{2/}}$
4	$1056 \times 0.253 = 267 \text{ ft}$	$1056 \times (4-1) + 267 = 3435 \text{ ft}$	$13.0 \times 0.515 = 6.7 \text{ ft}$
5	$1056 \times 0.040 = 42 \text{ ft}$	$1056 \times (5-1) + 42 = 4266 \text{ ft}$	$13.0 \times 0.101 = 1.3 \text{ ft}$

- 1/ The 0.1 ft offset for Core #1 was moved in to 0.3 ft due to the 4 in. minimum from the edge requirement.
- 2/ The 13.0 ft offset for Core #3 was move in to 12.7 ft due the 4 in. minimum from the edge requirement. Since this core is within 1 ft from an unconfined edge 2% will be added to the measured core density.

**PFP and QCP Random Density Procedure
Appendix E.3**

Effective: April 1, 2009
Revised: [April 27, 2017](#)

RANDOM NUMBERS

0.576	0.730	0.430	0.754	0.271	0.870	0.732	0.721	0.998	0.239
0.892	0.948	0.858	0.025	0.935	0.114	0.153	0.508	0.749	0.291
0.669	0.726	0.501	0.402	0.231	0.505	0.009	0.420	0.517	0.858
0.609	0.482	0.809	0.140	0.396	0.025	0.937	0.301	0.253	0.761
0.971	0.824	0.902	0.470	0.997	0.392	0.892	0.957	0.040	0.463
0.053	0.899	0.554	0.627	0.427	0.760	0.470	0.040	0.904	0.993
0.810	0.159	0.225	0.163	0.549	0.405	0.285	0.542	0.231	0.919
0.081	0.277	0.035	0.039	0.860	0.507	0.081	0.538	0.986	0.501
0.982	0.468	0.334	0.921	0.690	0.806	0.879	0.414	0.106	0.031
0.095	0.801	0.576	0.417	0.251	0.884	0.522	0.235	0.389	0.222
0.509	0.025	0.794	0.850	0.917	0.887	0.751	0.608	0.698	0.683
0.371	0.059	0.164	0.838	0.289	0.169	0.569	0.977	0.796	0.996
0.165	0.996	0.356	0.375	0.654	0.979	0.815	0.592	0.348	0.743
0.477	0.535	0.137	0.155	0.767	0.187	0.579	0.787	0.358	0.595
0.788	0.101	0.434	0.638	0.021	0.894	0.324	0.871	0.698	0.539
0.566	0.815	0.622	0.548	0.947	0.169	0.817	0.472	0.864	0.466
0.901	0.342	0.873	0.964	0.942	0.985	0.123	0.086	0.335	0.212
0.470	0.682	0.412	0.064	0.150	0.962	0.925	0.355	0.909	0.019
0.068	0.242	0.777	0.356	0.195	0.313	0.396	0.460	0.740	0.247
0.874	0.420	0.127	0.284	0.448	0.215	0.833	0.652	0.701	0.326
0.897	0.877	0.209	0.862	0.428	0.117	0.100	0.259	0.425	0.284
0.876	0.969	0.109	0.843	0.759	0.239	0.890	0.317	0.428	0.802
0.190	0.696	0.757	0.283	0.777	0.491	0.523	0.665	0.919	0.146
0.341	0.688	0.587	0.908	0.865	0.333	0.928	0.404	0.892	0.696
0.846	0.355	0.831	0.281	0.945	0.364	0.673	0.305	0.195	0.887
0.882	0.227	0.552	0.077	0.454	0.731	0.716	0.265	0.058	0.075
0.464	0.658	0.629	0.269	0.069	0.998	0.917	0.217	0.220	0.659
0.123	0.791	0.503	0.447	0.659	0.463	0.994	0.307	0.631	0.422
0.116	0.120	0.721	0.137	0.263	0.176	0.798	0.879	0.432	0.391
0.836	0.206	0.914	0.574	0.870	0.390	0.104	0.755	0.082	0.939
0.636	0.195	0.614	0.486	0.629	0.663	0.619	0.007	0.296	0.456
0.630	0.673	0.665	0.666	0.399	0.592	0.441	0.649	0.270	0.612
0.804	0.112	0.331	0.606	0.551	0.928	0.830	0.841	0.702	0.183
0.360	0.193	0.181	0.399	0.564	0.772	0.890	0.062	0.919	0.875
0.183	0.651	0.157	0.150	0.800	0.875	0.205	0.446	0.648	0.685

Note: Always select a new set of numbers in a systematic manner, either horizontally or vertically. Once used, the set should be crossed out.